

Product Description

Polyester Tape is a spun-bonded, non-woven, polyester-web tape.

Color

Off-White

FEATURES

» Excellent Reinforcement of Stress Areas

TYPICAL USES

» Polyester Tape is used in many Polydeck® decking systems Provides excellent reinforcement for

»

- Joints »
 - Cracks
- Seams

REVISION 04/12/18

»

»

»

- Flashings » Plywood
- Concrete »
 - **Other High Stress Areas**

PACKAGING

Single Rolls - 3" x 375' (76.2 cm x 114.3 meters) Sold Individually or in Cases of 12 Rolls

TECHNICAL DATA

Coverage per roll, length, observed	375 ft 114.3 meters
Thickness, observed	0.0087 in 0.22 mm
Average weight, observed	1.50 oz/sqm 51 gm/sqm
Grab Tensile, ASTM D-1682, Machine Direction Cross Machine Direction	44 psi (0.3 Mpa) 35 psi (0.2 Mpa)
Strip Elongation at Break, ASTM D-1682, Machine Direction Cross Machine Direction	52% 3%
Trapezoid Tear Strength, ASTM D-2263 Machine Direction Cross Machine Direction	18.5 lbs (8.4 kgs) 13.2 psi (6 kgs)
Mullen Burst, ASTM D-774 Fill	49 lbs 22.2 kgs



Disclaimer: All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the users responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein arela lot the manufacturer. Inclusion and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Polycoat Products All rights reserved.

POLYCOAT PRODUCTS TEL 562.802.8834 | FAX 562.921.7363 wpsales@polycoatusa.com | www.polycoatusa.com



....