

# TECHNICAL DATA SHEET | Section 11.3

# **SUPER SEALTAPE**

Pressure Sensitive Tape for Metals, Flashings, Plywood and Concrete Surfaces

REVISION 04/12/18

# **Product Description**

Super Seal Tape is a 9 mil thick, laminated, spun-bonded polyester substrate reinforced with hybrid polyester fibers. These fibers have been specifically created to provide high modulus of strength on initial impact. The adhesive is a highly aggressive acrylic system that delivers high tack and high shear strength. This product has an excellent adhesion to metal or wood. The adhesive has excellent cold temperature and condensation resistance with an extremely wide application gradient and a built-in ultra violet stabilizer system.

### Color

White

#### **PACKAGING**

Widths: 4", 8", 12", 16", 24" and 48" rolls (10.14 cm,

20.14cm, 30.48 cm, 60.96 cm, 121.29 cm)

Lengths: 180' (55 m)

#### **FEATURES**

- » Ultra-Violet Stable
- » Labor Saving
- User Friendly
- » Fast Tack Set
- Waterproof
- » Coating Ready
- » Compatible with Most Coatings
- » Field or Shop Applied to Substrates
- Adhesion to Most Common Construction Metals

#### TYPICAL USES

- » Balcony Flashing Tape
- » Roof Repair
- » Coatings Over Metal
- » Basements
- » Roofing Joints
- » Foundation Walls
- » Green Roof Waterproofing »
- Balcony and Breezeway Waterproofing

# TECHNICAL DATA

Base Material	Spun-Bonded Polyolefin
Fibers	Polyester Hybrid
Thickness	9 Mils (2.286 microns)
Tensile	1,000 lbs per inch
Elasticity	6%
Memory	98%
Temperature Resistance	10 to 250°F -4 to 121°C
Minimum Application Temperature	-23°C (-9.4°F)
Release Liner	90 GSM PE Liner
Adhesion to Galvanized Steel	28.5 lbs p/Lft @ RT 20 min Dwell
Adhesion to Copper	24.75 lbs p/Lft @ RT 20 min Dwell
Adhesion to Steel	32.25 lbs p/Lft @ RT 20 min Dwell
Adhesion to Aluminum	38.66 lbs p/Lft @ RT 20 min Dwell

Disclaimer: All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the users responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the product. We do not suggest or guarantee that any nazard issenting and hability featuring the product. We do not suggest or guarantee that any nazard issenting in hability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Polycoat Products makes no claim that these tests or any other tests, accurately represent all environments. © 2018 Polycoat Products. All rights reserved. POLYCOAT PRODUCTS TEL 562.802.8834 | FAX 562.921.7363 Section 11.3 wpsales@polycoatusa.com | www.polycoatusa.com

.... .... .... ••• ••••• .... . . . . . . . . . . . .

00000 . .