

REVISION 4/1/18

Product Description

Polyprime 3042 is a two component, liquid applied primer. This primer has been developed for use on carbon steel, non-ferrous metal, fiberglass, PVC pipe, as well as concrete and masonry.

FEATURES

- » Low Viscosity Epoxy Coating
- » Surface Tolerant Primer/Sealer
- » Provides Limited Chemical Resistance
- » Versatile Application: Spray, Roll or Brush

TYPICAL USES

- » Mining and Milling Industry
- » Petrochemical Plants
- » Pulp and Paper Industry
- » Chem. & Pharm. Industries
- » Steel Structures and Bridges
- » Food Processing Facilities
- » Concrete Floors and Decks
- » Power Generating Plants
- » Water & Wastewater Treatment Plants
- » Industrial Flooring

PACKAGING

3-Gallon Kit One 3.5 gallon pail, net fill 2 gallons (7.57 liters) of Side-A and One 1 gallon (3.78 liters) can of Side-B

15-Gallon Kit Two 5 gallon (18.9 liters) pails of Side-A and One 5 gallon (18.9 liters) pail of Side-B

Color

Side-A: Grey, Side-B: Clear

Coverage

The approximate coverage is 1 gallon/300 sqft (0.14 l/sqm) or 300 sqft/gallon. Coverage rate will depend on surface roughness and porosity.

Surface Preparation

In general, coating performance is directly proportional to surface preparation. All surfaces must be free of oil, grease,

TECHNICAL DATA (BASED ON DRAW DOWN FILM)

Coverage Rate 1 gal/300 sqft
0.14 l/sqm

Dry Film Thickness per Coat 4.5 ± 1 mils
102 ± 25 microns

Mixing Ratio 2A:1B

Pot Life at 75°F (24°C), 50% RH 20-30 min

Specific Gravity, Side-A 1.30 ± 0.1
Side-B 1.89 ± 0.1

Total Solids by Weight, ASTM D-2369 91 ± 2%

Total Solids by Volume, ASTM D-2697 90 ± 2%

Viscosity at 75°F (24°C) 1200 ± 200 cps

Volatile Organic Compounds, ASTM D-2369-81 0.75 lb/gal
90 gm/liters

dirt and other contaminants. Refer to General Guidelines for complete information.

Carbon Steel: Use SSSP Guidelines for surface preparation acceptable systems include SP-6 (Commercial Blast), SP-3 (Power Tool/Hand Tool). SSSP-SP-2, 3, 6 or SP-12 (WJ-3).

Aluminum: Remove oil, grease, dirt and other contaminants with neutral detergent and treat with Alondine® 1200 or equal. Light abrasive blasting is also acceptable.

Galvanized Steel: Remove all contaminants such as oil, grease, dirt or residues with a neutral detergent and treat with Galvaprep®. Light abrasive blasting is also acceptable.

Existing Coatings: Use SSSP guidelines for re-coating methods, recommended systems are SP-7 Abrasive blast or SP-3 Power Tool cleaning. Pressurized water at 2000 psi may also be used in conjunction with abrasive blasting or Power tool cleaning. Apply a test patch to check adhesion before



topcoating.

Concrete: Pressure wash (2000-3000 psi) with clean fresh water in conjunction with biodegradable cleanser if necessary to remove all contaminants. Surface shall be dry and free of all oils, wax or any loose sealers or coatings. Use SSSP guidelines for abrading the surface such as SP-7 Brush-off blast cleaning.

Apply over prepared or suitably prepared carbon steel, galvanized steel, concrete or aluminum.

Mixing

The volume mixing ratio is 2 parts Side-A to 1 part Side-B (2A:1B). Do not mix in an up and down motion.

Polyprime 3042 Side-A and Side-B should be thoroughly mixed individually prior to combining to ensure a homogeneous material. Polyprime 3042 must always be mixed with two parts Side-A and one part Side-B (2A:1B). The combined components should be thoroughly mixed using a mechanical mixer at slow speed.

Polyprime 3042 may be diluted with either PM Acetate or MEK within the regional air pollution regulations. Clean all application equipment with xylene, MEK or other appropriate solvents. Power stir product until uniform color appears, approximately 5 minutes.

Polyprime 3042 is very sensitive to heat and moisture. Higher temperature will accelerate the cure time. Use caution in batch sizes and thickness of application. Low temperature extends the cure time and the use of accelerators may be necessary.

Application

Polyprime 3042 should be applied at the rate of 1 gallon (mixture of Side-A & Side-B)/300 sqft (0.14 liters/sqm). Coverage rate will depend on surface roughness and porosity. It can be applied using an airless sprayer, brush, or phenolic resin core roller.

Application temperature for Polyprime 3042 should be between 60-95°F (15-35°C). Do not apply product unless temperature is at least 5° F (3°C) above the dew point. Re-coat schedule is 2-36 hours dependent upon environment. See Specification

Guide for re-coating guidelines and additional information.

Airless Spray: Use Graco 28:1 pump or higher, Binks "Airless" spray gun with Reversa-Clean 0.017-0.019 spray tips with a 1" fluid line, adjust pump pressure to the lowest possible setting that provides proper atomization. Equipment of equal performance is acceptable.

Conventional Spray: Variations of conventional production spray equipment such as pressure pot, air assisted, airless or high volume, low pressure systems as supplied by Binks, Graco, Nordson, Devilbiss or equal may be used. See Specification Guide for additional information.

Brush: Use mohair or natural bristle brush with feather edge.

Roller: Use phenolic core, short nap sheepskin or equal natural roller covers.

Cleanup

Equipment should be cleaned with an environmentally safe solvent, as permitted under local regulations, immediately after use.

Storage

Polyprime 3042 has a shelf life of 1 year from date of manufacture in original, factory-sealed containers when stored indoors at a temperature between 60-95°F (15-35°C).

Limitations

Polyprime 3042 should be coated within 36 hours after it has become tack free. Not UV stable. Surfaces must be dry, clean and free of foreign matter. Containers that have been opened must be used as soon as possible.

Polyprime 3042 is difficult to clean up after it has cured. Mix no more material than can be used within minutes.

Warning

This product contains Epoxy Resin and Curatives.

Disclaimer: All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the users responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Polycoat Products makes no claim that these tests or any other tests, accurately represent all environments. © 2018 Polycoat Products. All rights reserved.