

Product Description

Polycoat-Staingard 8072SC is an aliphatic polyaspartic, environmentally-friendly surface topcoat for waterproofing membrane systems. Polycoat-Staingard 8072SC is quick curing and specifically formulated to be installed in thin film applications. Polycoat Products manufactures products in different VOC's ranging from 100 to 340 gms/liter to comply with VOC requirement in various regions. Make sure to use the right grade of product which complies with VOC regulations/requirements applicable as per federal, state, statutory, counties, cities and local bodies at the place of installation.

FEATURES

- » Quick Cure
- » Very Durable
- » High Tensile Strength
- » High Gloss
- » Abrasion Resistant
- » Excellent Weatherability
- » Seamless Waterproofing Membrane
- » UV Resistant For Superior Gloss Retention

TYPICAL USES

- » Concrete
- » Plywood
- » Cold Storage Areas
- » Chemical Plants
- » Fertilizer Plants
- » Off-Shore Oil Platforms
- » Steel
- » Plastic
- » Food Processing Areas
- » Pulp and Paper Mills
- » Pipeline Barges
- » Industrial Warehouses

PACKAGING

2-gallon kit One 1 gallon (3.78 liters) can Side-A and One 1 gallon (3.78 liters) can Side-B

10-gallon kit One 5 gallon (18.9 liter) pail of Side-A and One 5 gallon (18.9 liter) pail of Side-B
10-gallon kit is not a stock item and is available with minimum order of 100 gallons (378 liters)

Color

Clear

Coverage

The approximate coverage is 1 gallon/100 sqft (0.41 l/sqm). Coverage rate will depend on surface roughness and porosity.

Surface Preparation

Surface must be clean, dry, and in sound condition. Remove

TECHNICAL DATA (BASED ON DRAW DOWN FILM)

Staingard 7072SC

Mix Ratio by Volume 1A : 1B

Coverage Rate 1 gal/100 sqft (0.41 l/sqm)

Dry Film Thickness per Coat 14 ± 2 mils
356 ± 50µ

Pot Life @ 75°F (24°C), 50% R.H. 40-45 minutes

Hardness, ASTM -2240 65 ± 5 Shore A

Tear Resistance, ASTM D-624 400 ± 20 pli
70.1 ± 8.8 kN/m

Tensile Strength, ASTM D-412 3500 ± 300 psi
24.1 ± 2.1 MPa

Ultimate Elongation, ASTM 412 50 ± 10%

Specific Gravity, Side A 1.07 ± 0.1
Side B 1.02 ± 0.1

Total Solids by Weight, ASTM D-2669 90 ± 2%

Total Solids by Volume, ASTM D-2697 88 ± 2%

Viscosity at 75°F (24°C), Side A 200 ± 50 cps
Side B 200 ± 50 cps

Volatile Organic Compounds, ASTM D-2369-81 0.83 lb/gal
100 gm/liters

all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion.

Refer to product General Guidelines for detailed surface preparation information.

Minimum recommended surface preparation:

METAL:

SSPC-SP6/NACE 3, 2 mils (50 microns) profile

CONCRETE & MASONRY:

SSPC-SP13/NACE 6 or ICRI No. 310.2 CSP 3-5. Primer required.

Mixing

Polycoat-Staingard 8072SC may not be diluted under any circumstance. Polycoat-Staingard 8072SC Side-A and Side-B should be mixed individually before combining. Add Side-B to Side-A while mixing, using a mechanical mixer at medium speed. Mix until a homogeneous mixture and color is attained (at least 5 minutes) and mix frequently during application to maintain uniform color. Use care to scrape the sides of the container to ensure that no unmixed material remains. Use caution no to whip air into the material as this may result in pinhole blisters and/or shortened pot life.

Do not mix in an up and down motion. Do not mix any material that cannot be used with 45 minutes.

Application

Polycoat-Staingard 8072SC can be applied by phenolic resin core roller, high pressure spray, or through a cup gun under low pressure. Polycoat-Staingard 8072SC should be applied at a minimum film thickness of 5 mils. It should be noted that the heavier the application, the longer the curing process takes.

Apply Polycoat-Staingard 8072SC evenly over the entire deck. For best results, use an airless sprayer. A phenolic resin core roller may be used, but extra care should be taken not to cause air bubbles.

Curing

At 75°F (24°C) and 50% relative humidity, allow each coat to cure 2-4 hours.

Allow 6 hours before permitting light pedestrian traffic and at least 24-48 hours before permitting heavy pedestrian traffic on to the finished surface.

Uncured Polycoat-Staingard 8072SC is very sensitive to heat and moisture. Higher temperatures and/or high humidity will accelerate the cure time. Use caution in batch sizes and thickness of application. If more than 12 hours have passed after applying clear coat of Polyaspartic, then re-prime surface with Polyprime U and apply Polycoat Staingard pigmented coat. If clear coat is required, then clear coat should be applied only after pigmented coat. If clear coat is applied after primer, the primer will become yellowish with exposure to light and surface will look not look aesthetically pleasing.

Low temperature and/or low humidity extend the cure time.

Cleanup

Equipment should be cleaned with an environmentally safe solvent, as permitted under local regulations, immediately after use.

Storage

Polycoat-Staingard 8072SC has a shelf life of one (1) year from date of manufacture in original, factory-sealed containers when stored indoors at a temperature between 60-95°F (15-35°C).

Limitations

The following conditions must not be coated with Polycoat deck coatings or systems: split slabs, buried membrane, sandwich slabs with insulation, slabs over unvented metal pan, magnesite, and non-structural lightweight concrete. On grade slabs may receive Polycoat system coatings provided a moisture-vapor transmission test is first performed. Please contact Polycoats' technical department with the results.

With regard to coating asphalt surfaces, please contact Polycoats' technical department.

Surfaces must be dry, clean and free of foreign matter. Clear coating may turn opaque and cloudy due to moisture penetration, especially in exterior applications. Surface may be slippery when wet. Containers that have been opened must be used as soon as possible. Do not dilute under any circumstance.

Warning

This product contains Isocyanates and Solvent.

Disclaimer: All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the users responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Polycoat Products makes no claim that these tests or any other tests, accurately represent all environments. © 2018 Polycoat Products. All rights reserved.