

CLIENT: POLYCOAT PRODUCTS

14722 Spring Avenue
Santa Fe Springs, CA 90770
Hemant Prajapati

Test Report No: RJ1292-2

Date: April 13, 2011

SAMPLE ID: The test samples are identified as specimens of Polyeuro MH 752 FR coating applied to cement board substrate.

SAMPLING DETAIL: Test samples were submitted to the laboratory directly by the client. No special sampling conditions or sample preparation were observed by QAI.

DATE OF RECEIPT: Samples were received at QAI on April 7, 2011.

TESTING PERIOD: March 31, 2011.

AUTHORIZATION: Testing authorized by Hemant Prajapati.

TEST REQUESTED: Perform standard flame spread and smoke density developed classification tests on the sample supplied by the Client in accordance with ASTM Designation E84-09, "Standard Method of Test for Surface Burning Characteristics of Building Materials". The foregoing test procedure is comparable to UL 723, ANSI/NFPA No. 255, and UBC No. 8-1.

TEST RESULTS:	<u>Flame Spread</u>	<u>Smoke Developed</u>
	20	120

Detailed test results are presented in the subsequent pages of this report

Prepared By



Brian Ortega
Test Technician

**Signed for and on behalf of
QAI Laboratories, Inc.**



Greg Banasky
Senior Test Technician



PREPARATION AND CONDITIONING: The sample material was submitted in five pieces, 22" wide by 60" long.

Prior to testing, the specimen was placed in the conditioning room (maintained at $73.4 \pm 5^\circ$ F and a relative humidity of $50 \pm 5\%$) and allowed to reach moisture equilibrium.

E 84 TEST DATA SHEET:

CLIENT: Polycoat Products **Date:** 04/07/11

SAMPLE: Polyeuro MH 752 FR coating applied to cement board substrate

FLAME SPREAD:

IGNITION: 1 minute, 12 seconds

FLAME FRONT: 6 feet Maximum.

TIME TO MAXIMUM SPREAD: 9 minute, 39 seconds.

TEST DURATION: 10 minutes.

CALCULATION: $35.53 \times 0.515 = 18.30$

SUMMARY: FLAME SPREAD: 20 SMOKE DEVELOPED: 120

SUMMARY OF ASTM E84 RESULTS: Because of the possible variations in reproducibility, the results are adjusted to the nearest figure divisible by 5. Smoke Density values over 200 are rounded to the nearest figure divisible by 50.

In order to obtain the Flame Spread Classification, the above results should be compared to the following table:


<u>NFPA CLASS</u>	<u>IBC CLASS</u>	<u>FLAME SPREAD</u>	<u>SMOKE DEVELOPED</u>
A	A	0 through 25	Less than or equal to 450
B	B	26 through 75	Less than or equal to 450
C	C	76 through 200	Less than or equal to 450

BUILDING CODES CITED:


1. National Fire Protection Association, ANSI/NFPA No. 101, "Life Safety Code", 2006 Edition.
2. International Building Code, 2006 Edition, Chapter 8, Interior Finishes, Section 803.

THIS REPORT IS THE CONFIDENTIAL PROPERTY OF THE CLIENT ADDRESSED. THE REPORT MAY ONLY BE REPRODUCED IN FULL. PUBLICATION OF EXTRACTS FROM THIS REPORT IS NOT PERMITTED WITHOUT WRITTEN APPROVAL FROM QAI. ANY LIABILITY ATTACHED THERETO IS LIMITED TO THE FEE CHARGED FOR THE INDIVIDUAL PROJECT FILE REFERENCED. THE RESULTS OF THIS REPORT PERTAIN ONLY TO THE SPECIFIC SAMPLE(S) EVALUATED.

FLAME SPREAD



SMOKE DEVELOPED



THIS REPORT IS THE CONFIDENTIAL PROPERTY OF THE CLIENT ADDRESSED. THE REPORT MAY ONLY BE REPRODUCED IN FULL. PUBLICATION OF EXTRACTS FROM THIS REPORT IS NOT PERMITTED WITHOUT WRITTEN APPROVAL FROM QAI. ANY LIABILITY ATTACHED THERETO IS LIMITED TO THE FEE CHARGED FOR THE INDIVIDUAL PROJECT FILE REFERENCED. THE RESULTS OF THIS REPORT PERTAIN ONLY TO THE SPECIFIC SAMPLE(S) EVALUATED.