



**POLYCOAT
PRODUCTS**
A Division of American Polymers Corp.

THEMECOAT™ 1752
*Two Component Aromatic Hybrid
Polyurethane Hard Coat
Technical Data Sheet*

DESCRIPTION

Themecoat™ 1752 is a fast set, rapid curing, aromatic, two component, hybrid polyurea/polyurethane spray designed to be applied over EPS, wood and many other surfaces. It's excellent balance of stiffness and impact resistance provides excellent plastic "shell-like" protection for delicate foams and EPS. Themecoat™ 1752's chemical design allows fast "user-friendly" application with excellent flow and appearance.

FEATURES

- ❖ Plastic "Shell-Like" Protection
- ❖ 100% Solids
- ❖ Excellent Thermal Stability
- ❖ Excellent Chemical Protection
- ❖ Excellent Cold Temperature Impact
- ❖ Low Shrinkage
- ❖ Zero VOC
- ❖ Fast Cure
- ❖ High Productivity
- ❖ High Gloss

TYPICAL USES

- ❖ EPS Hard Coat Surface Protection
- ❖ Decorations
- ❖ Architectural Shapes

COLORS

Neutral. Custom colors are available upon request.

PACKAGING

100 gallon kit: One 50 gallon drum of Part-A and one 50 gallon drum of Part-B.

COVERAGE

Themecoat™ 1752 should be applied in thin passes to achieve desired thickness. Theoretical coverage for 1 mil thickness is one gallon per 1600 sq. ft.

SURFACE PREPARATION

Remove all contaminant, oil and grease from substrate.

MIXING

Themecoat™ 1752 may not be diluted under any circumstances. Thoroughly mix Themecoat™ 1752 Part-B Base material with air driven power equipment until a homogeneous mixture and color is obtained.

APPLICATION

Themecoat™ 1752 should be applied using a 1:1 plural component equipment capable of developing a minimum of 2000 psi (13.8 MPa) and heating the individual component to **170°F (77°C)** using an impingement gun.

Hose temperature should be maintained at **160-170°F (72-77°C)**. The Themecoat™ 1752 material should be preheated to **75-85°F (24-29°C)**.

Themecoat™ 1752 should be sprayed in multidirectional passes for a proper uniform thickness.

TECHNICAL DATA

Mix Ratio by Volume	1A : 1B
Pot Life	5-7 seconds
Tack Free Time	60-120 seconds
Recoat Time	0-6 hours
Viscosity at 150-160°F (66.5-71°C), Brookfield:	
Part-A	90 ± 20 cps
Part-B	160 ± 20 cps
Density (Side A & B Combined)	9.03 lbs/gal
Flash Point	>200°F
	>93.3°C
Hardness, ASTM D-2240	75 ± 5 D
Tensile Strength, ASTM 412-C	3700 ± 200 psi
	25.5 ± 1.4 MPa
Elongation, ASTM 412-C	40% ± 20%
Tear, ASTM 624-C	450 ± 50 pli
Service Temperature	-20°F to 250°F
	-29°C to 121°C

(*These physical properties from sample sprayed with Graco Foam Cat 200 @ 2000 psi (13.8 MPa) minimum, with Gusmer GX7-400 mechanical purge gun @ 150-160°F (65-71°C). Different machine and parameter will change these properties. User should perform their own independent testing as properties are approximate.)

EQUIPMENT CLEAN UP

Equipment should be cleaned with an environmentally safe, urethane-grade solvent (alcohol free) as permitted under local regulations immediately after use.

STORAGE

Themecoat™ 1752 has a shelf life of six (6) months from date of manufacture in factory sealed containers.

Part-A and Part-B drums must be stored above 60°F (15°C).

Avoid freezing temperatures.

Store drums on wooden pallets to avoid direct contact with the ground.

If stored for a long period of time, rotate Part-A and Part-B drums regularly.

Do not open until ready to use.

WARNING

This product contains Isocyanates and Curative Material.

Please read all information in the general guidelines, product data sheets, guide specifications and material safety data sheets (MSDS) before applying material. Published technical data and instructions are subject to change without notice. Contact your local Polycoat Products representative or visit our website for current technical data and instructions.

LIMITED WARRANTY

Polycoat Products warrants its products to be free of manufacturing defects and that they will meet Polycoat Products current published physical properties. Polycoat Products warrants that its products, when properly installed by a state licensed waterproofing contractor according to Polycoat Products guide specifications and product data sheets over a sound, properly prepared substrate, will not allow water migration for a period of one (1) year. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. There are no other warranties by Polycoat Products of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. Polycoat Products shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. Polycoat Products shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. Polycoat Products reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

DISCLAIMER

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the users responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Polycoat Products makes no claim that these tests or any other tests, accurately represent all environments.