

REVISION 03/26/20

The following are general guidelines for re-coating both Polycoat and other similar polyurethane deck coating systems. Specific re-coating procedures will be determined only after a thorough inspection of the existing coating system that is to be re-coated.

1. Pressure-wash the existing polyurethane coating with a suitable cleaning agent such as TSP and water to degrease and remove all foreign matter, dirt, debris, and loose coating. A citrus based or other more stringent cleaner may be required for removal of stubborn grease stains. Thoroughly rinse to remove all cleaning residue.
2. Completely remove all striping paint (on parking decks).
3. Perform all necessary crack and spall repairs, if any, per manufacturer's standard recommendations.
4. Perform an adhesion test(s) as necessary.
5. Patch all exposed substrate with basecoat such as PC-260. Abrade exposed concrete substrate to create an ICRI CSP 3 profile for pedestrian decks and CSP 4-5 profile for vehicular decks if necessary and prime with Polyprime® 21 or 2180 prior to patching; Polyprime® U may be used in pedestrian deck applications.
6. Prime the existing coating with the appropriate Polycoat re-coat primer.

**Options**

- a. Apply an intermediate coat with sand followed by application of a topcoat.
- b. Apply a topcoat with sand and back roll.
- c. Apply a complete deck coating system.

### **Pedestrian Deck Re-Coat Procedure**

1. Pressure-wash the existing polyurethane coating with a suitable cleaning agent such as TSP and water to degrease and remove all foreign matter, dirt, debris, and loose coating. A citrus based or other more stringent cleaner may be required for removal of stubborn grease stains. Thoroughly rinse to remove all cleaning residue.
2. Perform all necessary crack and spall repairs, if any, per manufacturer's standard recommendations.
3. Perform an adhesion test(s) as necessary.
4. Patch all exposed substrate with basecoat such as PC-260. Abrade exposed concrete substrate to create an ICRI CSP 3 profile for pedestrian decks and CSP 4-5 profile for vehicular decks if necessary and prime with Polyprime® U at a rate of 1 gal/150 sqft or 150 sqft/gallon and broadcast aggregate at desired rate into wet primer.
5. Apply Polyglaze™ 100 at 1 1/4 gallons/100 sqft or 80 sqft/gallon (0.51 liters/sqm).

**Note:** Polycoat will issue a 5 year product warranty for this application premised on the existing coating being in sound condition.

### **Vehicular Deck Re-Coat Procedure**

1. Pressure-wash the existing polyurethane coating with a suitable cleaning agent such as TSP and water to degrease and remove all foreign matter, dirt, debris, and loose coating. A citrus based or other more stringent cleaner may be required for removal of stubborn grease stains. Thoroughly rinse to remove all cleaning residue.
2. Completely remove all striping paint (on parking decks).
3. Abrade all exposed concrete to render a CSP 4-5 profile.
4. Perform all necessary crack and spall repairs, if any, per manufacturer's standard recommendations.
5. Perform an adhesion test(s) as necessary.
6. Patch all exposed substrate with basecoat such as PC-260. Abrade exposed concrete substrate to create an ICRI CSP 3 profile for pedestrian decks and CSP 4-5 profile for vehicular decks if necessary and prime with Polyprime® 21 or 2180 prior to patching; Polyprime® U may be used in pedestrian deck applications.
7. Prime the existing coating with the appropriate Polycoat re-coat primer.
8. Apply Poly-I-Gard® 246 Vehicular Deck Coating System per manufacturer's system data sheet.

© 2025 Polycoat Products. All rights reserved.



**Limited Warranty:** Please read all information in the General Guidelines, Technical Data Sheets, Guide Specifications and Safety Data Sheets (SDS) before applying material. These Products are for "Professional Use Only" and preferably applied by professionals who have prior experience with the Polycoat Products materials or have undergone training in application of Polycoat Products materials. Published technical data and instructions are subject to change without notice. Contact your local Polycoat Products representative or visit our website for current technical data, instructions, and project specific recommendations.

Polycoat Products warrants its products to be free of manufacturing defects and that they will meet Polycoat Products current published physical properties. Polycoat Products warrants that its products, when properly installed by a state licensed waterproofing contractor according to Polycoat Products guide specifications and product data sheets over a sound, properly prepared substrate, will not allow water migration for a period of one (1) year. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. There are no other warranties by Polycoat Products of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. Polycoat Products shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. Polycoat Products shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. Polycoat Products reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

**Disclaimer:** All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the users responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Polycoat Products makes no claim that these tests or any other tests, accurately represent all environments.

