

GREATER LOS ANGELES-14722 Spring Avenue - Santa Fe Springs, CA 90670 DALLAS / FT.WORTH METROPLEX-2100 Reliance Parkway - Bedford, TX 76021

Tel: (562) 802-8834 Fax: (562) 921-7363 www.Polycoat.com

TECHNICAL DATA SHEET

PCF 2131-FR-7.5-50S-NAT

Rigid Polyurethane Foam System

Typical Properties PCF 2131-FR A-Comp (ISO)

Viscosity, mPa·s @ 25°C: 200-250 Lbs/gal 10.33 Specific Gravity @ 25°C : 1.24 Appearance @ 25°C: liquid

Typical Properties PCF 2131-FR- B-Comp (polyol blend)

 Viscosity, mPa·s @ 25°C:
 1800-2500

 Lbs/gal
 8.69

 Specific Gravity @ 25°C :
 1.04

Appearance @ 25°C: viscous liquid

Product Description:

PCF 2131-FR polyurethane foam systems are designed for molding and void filling applications. PCF 2131-FR-5 can be designed to meet a variety of reactivity requirements without sacrificing product quality and can be formulated to a wide range of densities from 3 to 30 pounds per cubic foot. The unique handling characteristics of the PCF 2131 series systems provide ease of mixing by hand or machine to produce a uniform product with excellent cell structure. This product does not contain any CFC blowing agent or other Ozone Depleting chemical. The PCF 2131-FR series systems have been formulated for use as a high compressive strength rigid foam for the manufacturing of molded picture frames, furniture parts, structural floats and other design applications. This product contains flame retardant for the purpose of self—extinguish.

Storage and Handling:

Containers for both A and B components should be kept tightly closed to prevent moisture contamination. Do not reseal if contamination is suspected. Use of a dry nitrogen blanket for partial drums is recommended. Component B may be stored at ambient temperatures. Storage for

Component A should be maintain between 77°F (25°C) and 95°F (35°C). An additional note of caution is that exposure to temperatures over 400°F (204°C) can create excessive pressure potentially causing containers to rupture. Do not breathe aerosol or vapors and avoid contact with skin and eyes. Exposure to vapors of heated MDI can be dangerous. To heat product properly, use well ventilated convection ovens or other methods that distribute heat evenly. Avoid using drum heaters or other heat sources that may cause excessive local heating.

Rise Time

Demold Time

Health and Safety Information:

Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling any of the products listed above. Before working with these products, it is your responsibility to read and become familiar with the available information on its hazards, proper use and handling. This is extremely important and cannot be overemphasized. Information is available in several forms, e.g. material safety data sheets and product labels. To obtain this information, contact yours Polycoat Product representative.

is up to the User to contact Polycoat Products to verify the correctness prior to ordering or specifying this product. Polycoat Products warrants this product for merchantable quality only, does not warranty against unknown risks that may or may not be present, nor do we assume any responsibility for coverage, performance, or injuries resulting from the use of this product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY POLYCOAT PRODUCTS EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OR LAW, OR OTHERWISE, INCLUDING MARKETABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Failure to strictly adhere to recommended procedures shall relieve Polycoat Products of all liability with respect to the product or the use thereof. The buyer assumes all risks whatsoever as to the use of these products and the Buyer's exclusive remedy as to any breach of warranty or negligence claim shall be limited to the purchase price of the materials and agrees that any and all litigation proceedings shall be according to the laws of California and shall be filed in the County of Santa Fe Springs, CA. Each person, firm, or corporation engaged in the application installation, disposal or any other use of the any of these products shall carefully determine whether there is a potential hazard associated with such product in a specific usage, and utilize all appropriate precautionary and safety measures as outlined in Local, State and Federal regulations governing the use or disposal of these products or the construction and/or renovation of structures.
--

Torrigal Disprisal Desperties				
Typical Physical Properties	ı			
Density, pcf	AS	ГМ D-1638	7.5	
Compressive Strength, psi	AS	ΓM D-1621	140	
Tensile strength, psi	AST	ГМ D-1623	160	
Shear Strength, psi	AS	TM C-273	75	
Processing Characteristics @ 74 ° F				
Ratio, By volume A/B			50/50	
Cream Time		Sec	53-60	

Sec.

Min.

180-270

5-20