

NELSON

TESTING
LABORATORIES

EXPERIENCED | INNOVATIVE | AUTHENTIC

**Elastomeric Waterproofing Traffic-Bearing Membrane
ASTM C957 Evaluation**

for

Polycoat Products

**Polydeck 575FC
Traffic Deck System**

**Polycoat Products
14722 Spring Avenue
Santa Fe Springs, California 90670**

August 19, 2016

August 19, 2016

Polycoat Products
14722 Spring Avenue
Santa Fe Springs, California 90670

REPORT OF TESTS

SUBJECT: **Physical Analysis of Waterproofing Membrane**

PROJECT: **Polydeck 575FC Traffic Deck System**

SPECIFICATION: ASTM C957-15, "Standard Specification for High-Solids Content, Cold Liquid-Applied Elastomeric Waterproofing Membrane With Integral Wearing Surface"

TEST METHODS: ASTM C501, "Standard Test Method for Relative Resistance to Wear of Unglazed Ceramic Tile by the Taber Abraser"

ASTM C794, "Standard Test Method for Adhesion-in-Peel of Elastomeric Joint Sealants"

ASTM C1305, "Standard Test Method for Crack Bridging Ability of Liquid-Applied Waterproofing Membrane"

ASTM D412, "Standard Test Methods for Vulcanized Rubber and Thermoplastic Elastomers—Tension"

ASTM D471, "Standard Test Method for Rubber Property—Effect of Liquids"

ASTM D6511, "Standard Test Methods for Solvent Bearing Bituminous Compounds"

MATERIALS: Delivered to NTL in April 2016

NTL PROJECT #: 16-1088(D)

PAGE: 1 of 12

August 19, 2016
Polycoat – Polydeck 575FC Traffic Deck System
NTL Project #16-1088(D)
Page 2 of 12

TEST DATA

System: **Polydeck 575FC Traffic Deck System**

Components:

Primer:	Polyprimer EBF LV – 1 gallon / 300 sq. ft.
Base Coat:	PC 260 – 1.5 gallons / 100 sq. ft.
Top Coat:	Poly-I-Gard 295 – 1.5 gallons / 100 sq. ft. with sand broadcast @ 10 lbs / 100 sq.ft (backrolled)

August 19, 2016
Polycoat – Polydeck 575FC Traffic Deck System
NTL Project #16-1088(D)
Page 3 of 12

TEST RESULTSA. ASTM D6511 – Weight Loss of Base Coat (modified per ASTM C957, section 5.11)

Test Date: May 2016
Material: Basecoat - PC 260
Duration: 72 hours

Results: **PASS**

	<u>PC 260</u>	<u>ASTM C957-15</u>
Weight Loss	5.5%	<i>40% max.</i>

August 19, 2016
Polycoat – Polydeck 575FC Traffic Deck System
NTL Project #16-1088(D)
Page 4 of 12

TEST RESULTS

B. ASTM C1305 – Crack Bridging (modified per ASTM C957, section 5.5)

Cast Date:	May 2016
Specimens:	Five assemblies
Application:	Primer – Polyprime EBF LV Basecoat – PC 260 Top Coat – Poly-I-Gard 295 with sand backrolled
Test Conditions:	-15 deg. F.
Duration:	10 cycles

Results: **PASS**

Polydeck 575FC System

ASTM C957-15

Crack Bridging @
10 Cycles

Specimen 1	no cracking @ 10 cycles
Specimen 2	no cracking @ 10 cycles
Specimen 3	no cracking @ 10 cycles
Specimen 4	no cracking @ 10 cycles
Specimen 5	no cracking @ 10 cycles

AVERAGE	no cracking @ 10 cycles	<i>no cracking</i>
---------	--------------------------------	--------------------

August 19, 2016
Polycoat – Polydeck 575FC Traffic Deck System
NTL Project #16-1088(D)
Page 5 of 12

TEST RESULTS (continued)

C. ASTM C794 – Adhesion in Peel (modified per ASTM C957, section 5.6)

Cast Date: May 2016
Specimens: Four specimens per test applied over mortar and plywood
Application: Primer – Polyprime EBF LV
Basecoat – PC 260
Curing: 14 days at 73 deg F., then 7 days at 158 deg. F. before immersion
Immersion Duration: 7 days

Results: **PASS**

Polyprime EBF LV/PC 260

ASTM C957-15

Adhesion – Cement Mortar

Specimen 1	25.8 lbf.
Specimen 2	18.0 lbf.
Specimen 3	22.0 lbf.
Specimen 4	29.2 lbf.

AVERAGE **23.8 lbf**

5.0 lbf. min.

Adhesion – Plywood

Specimen 1	16.2 lbf.
Specimen 2	20.7 lbf.
Specimen 3	24.7 lbf.
Specimen 4	24.7 lbf.

AVERAGE **21.6 lbf**

3.0 lbf. min.

August 19, 2016
Polycoat – Polydeck 575FC Traffic Deck System
NTL Project #16-1088(D)
Page 6 of 12

TEST RESULTS (continued)

D. ASTM D471 – Chemical Resistance (modified per ASTM C957, section 5.7)

Cast Date: May 2016
Specimens: Five dumbbells per test (Die C)
Application: PC 260
Curing: 21 days at 73 deg F. before chemical immersion
Immersion Duration: 336 hours

Results: **PASS**

	<u>PC 260</u>	<u>ASTM C957-15</u>
Tensile Retention (Water Immersion)		
Specimen 1	140%	
Specimen 2	98%	
Specimen 3	103%	
Specimen 4	118%	
Specimen 5	89%	
AVERAGE	110%	70%, min.
Tensile Retention (Ethylene Glycol)		
Specimen 1	104%	
Specimen 2	95%	
Specimen 3	68%	
Specimen 4	127%	
Specimen 5	70%	
AVERAGE	93%	70%, min.
Tensile Retention (Mineral Spirits)		
Specimen 1	83%	
Specimen 2	120%	
Specimen 3	111%	
Specimen 4	108%	
Specimen 5	123%	
AVERAGE	109%	45%, min.

August 19, 2016
Polycoat – Polydeck 575FC Traffic Deck System
NTL Project #16-1088(D)
Page 7 of 12

TEST RESULTS (continued)

D. ASTM D471 – Chemical Resistance (modified per ASTM C957, section 5.7) - continued

Cast Date: May 2016
Specimens: Five dumbbells per test (Die C)
Application: Poly-I-Gard 295
Curing: 21 days at 73 deg F. before chemical immersion
Immersion Duration: 336 hours

Results: **PASS**

	<u>Poly-I-Gard 295</u>	<u>ASTM C957-15</u>
Tensile Retention (Water Immersion)		
Specimen 1	107%	
Specimen 2	94%	
Specimen 3	104%	
Specimen 4	99%	
Specimen 5	41%	
AVERAGE	89%	70%, min.
Tensile Retention (Ethylene Glycol)		
Specimen 1	66%	
Specimen 2	49%	
Specimen 3	116%	
Specimen 4	86%	
Specimen 5	57%	
AVERAGE	75%	70%, min.
Tensile Retention (Mineral Spirits)		
Specimen 1	135%	
Specimen 2	99%	
Specimen 3	99%	
Specimen 4	50%	
Specimen 5	107%	
AVERAGE	98%	45%, min.

August 19, 2016
Polycoat – Polydeck 575FC Traffic Deck System
NTL Project #16-1088(D)
Page 8 of 12

TEST RESULTS (continued)

E. ASTM C957 – Weathering Resistance and Recovery from Elongation

Cast Date: May 2016
Specimens: Twenty dumbbell specimens per test (Die C)
Application: Primer – Polyprime EBF LV
Basecoat – PC 260
Top Coat – Poly-I-Gard 295*
*(*no aggregate included per ASTM C957)*
Curing: 21 days at 73 deg F., then 7 days at 158 deg. F. before cutting
Weathering: 500 hours - fluorescent UV

Results: **PASS**

Polydeck 575FC System ASTM C957-15

Recovery from Elongation, Initial

Specimen 1	100%	
Specimen 2	100%	
Specimen 3	100%	
Specimen 4	95%	
Specimen 5	100%	
Specimen 6	100%	
Specimen 7	95%	
Specimen 8	100%	
Specimen 9	100%	
Specimen 10	100%	
AVERAGE	99%	90%, min.

August 19, 2016
Polycoat – Polydeck 575FC Traffic Deck System
NTL Project #16-1088(D)
Page 9 of 12

TEST RESULTS (continued)

E. ASTM C957 – Weathering Resistance and Recovery from Elongation (continued)

Cast Date: May 2016
Specimens: Twenty dumbbell specimens per test (Die C)
Application: Primer – Polyprime EBF LV
Basecoat – PC 260
Top Coat – Poly-I-Gard 295*
*(*no aggregate included per ASTM C957)*
Curing: 21 days at 73 deg F., then 7 days at 158 deg. F. before cutting
Weathering: 500 hours - fluorescent UV

Results: **PASS**

Polydeck 575FC System ASTM C957-15

Tensile Retention

Specimen 1	57%	
Specimen 2	154%	
Specimen 3	124%	
Specimen 4	144%	
Specimen 5	87%	
Specimen 6	48%	
Specimen 7	168%	
Specimen 8	106%	
Specimen 9	106%	
Specimen 10	82%	
AVERAGE	108%	80%, min.

August 19, 2016
Polycoat – Polydeck 575FC Traffic Deck System
NTL Project #16-1088(D)
Page 10 of 12

TEST RESULTS (continued)

E. ASTM C957 – Weathering Resistance and Recovery from Elongation (continued)

Cast Date: May 2016
Specimens: Twenty dumbbell specimens per test (Die C)
Application: Primer – Polyprime EBF LV
Basecoat – PC 260
Top Coat – Poly-I-Gard 295*
*(*no aggregate included per ASTM C957)*
Curing: 21 days at 73 deg F., then 7 days at 158 deg. F. before cutting
Weathering: 500 hours - fluorescent UV

Results: **PASS**

Polydeck 575FC System ASTM C957-15

Elongation Retention

Specimen 1	41%	
Specimen 2	122%	
Specimen 3	106%	
Specimen 4	114%	
Specimen 5	98%	
Specimen 6	49%	
Specimen 7	122%	
Specimen 8	130%	
Specimen 9	114%	
Specimen 10	98%	
AVERAGE	99%	<i>90%, min.</i>

August 19, 2016
Polycoat – Polydeck 575FC Traffic Deck System
NTL Project #16-1088(D)
Page 11 of 12

TEST RESULTS (continued)

F. ASTM C501 – Abrasion Resistance (modified per ASTM C 957, section 5.9)

Cast Date: May 2016
Specimens: Three 4 x 4-in specimens
Application: Primer – Polyprime EBF LV
Basecoat – PC 260
Top Coat – Poly-I-Gard 295*
*(*no aggregate included per ASTM C957)*
Curing: 14 days at 73 deg F., then 7 days at 158 deg. F. before testing
Duration: 1,000 cycles with CS-17 abrasion wheel

Results: **PASS**

Polydeck 575FC System ASTM C957-15

Mass Loss @ 1,000 cycles

Specimen 1	5 mg.	
Specimen 2	5 mg.	
Specimen 3	10 mg.	
AVERAGE	7 mg.	50 mg. max.

August 19, 2016
Polycoat – Polydeck 575FC Traffic Deck System
NTL Project #16-1088(D)
Page 12 of 12

SUMMARY

The test results reported above from the Polydeck 575FC Traffic Deck System met or surpassed the corresponding requirements as listed in ASTM C957-15, Table 1.

Respectfully submitted,

NELSON TESTING LABORATORIES



Mark R. Nelson
President