



POLYCOAT PRODUCTS

A Division of American Polymers Corp.

GREATER LOS ANGELES-14722 Spring Avenue - Santa Fe Springs, CA 90670
DALLAS / FT.WORTH METROPLEX-2100 Reliance Parkway - Bedford, TX 76021

Tel: (562) 802-8834
Fax: (562) 921-7363

www.Polycoat.com

PRODUCT DATA SHEET

PCF 2221-5-CL1-55S NAT

Rigid Polyurethane Foam System

Typical Properties PCF 2221-5 CL1 A-Comp (ISO)

Viscosity, mPa-s @ 25°C:	200-250
Lbs/gal	10.33
Specific Gravity @ 25°C :	1.24
Appearance @ 25°C:	liquid

Typical Properties PCF 2221-5 CL1 B-Comp (polyol blend)

Viscosity, mPa-s @ 25°C:	700-900
Lbs/gal	9.83
Specific Gravity @ 25°C :	1.13
Appearance @ 25°C:	viscous liquid

Product Description:

PCF 2221-5-Class I is a two-component polyurethane foam system developed for Class I applications with all water blown foam. This system exhibits excellent flowability and dimensional stability for pour-in-place applications such as panel manufacturing.

Storage and Handling:

Containers for both A and B components should be kept tightly closed to prevent moisture contamination. Do not reseal if contamination is suspected. Use of a dry nitrogen blanket for partial drums is recommended. Component B may be stored at ambient temperatures. Storage for Component A should be maintained between 77°F (25°C) and 95°F (35°C). An additional note of caution is that exposure to temperatures over 400°F (204°C) can create excessive pressure potentially causing containers to rupture. Do not breathe aerosol or vapors and avoid contact with skin and eyes. Exposure to vapors of heated MDI can be dangerous. To heat product properly, use well ventilated convection ovens or other methods that distribute heat evenly. Avoid using drum heaters or other heat sources that may cause excessive local heating.

Health and Safety Information:

Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling any of the products listed above. Before working with these products, it is your responsibility to read and become familiar with the available information on its hazards, proper use and handling. This is extremely important and cannot be overemphasized. Information is available in several forms, e.g. material safety data sheets and product labels. To obtain this information, contact your Polycoat Products representative.

WARRANTY: The information herein is believed to be accurate and reliable as of the date of issuance, but is subject to change without prior notice. It is up to the User to contact Polycoat Products to verify the correctness prior to ordering or specifying this product. Polycoat Products warrants this product for merchantable quality only, does not warranty against unknown risks that may or may not be present, nor do we assume any responsibility for coverage, performance, or injuries resulting from the use of this product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY POLYCOAT PRODUCTS EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OR LAW, OR OTHERWISE, INCLUDING MARKETABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Failure to strictly adhere to recommended procedures shall relieve Polycoat Products of all liability with respect to the product or the use thereof. The buyer assumes all risks whatsoever as to the use of these products and the Buyer's exclusive remedy as to any breach of warranty or negligence claim shall be limited to the purchase price of the materials and agrees that any and all litigation proceedings shall be according to the laws of California and shall be filed in the County of Santa Fe Springs, CA. Each person, firm, or corporation engaged in the application installation, disposal or any other use of the any of these products shall carefully determine whether there is a potential hazard associated with such product in a specific usage, and utilize all appropriate precautionary and safety measures as outlined in Local, State and Federal regulations governing the use or disposal of these products or the construction and/or renovation of structures.

Typical Physical Properties

Density, pcf	ASTM D-1638	4.5-5.0
Compressive Strength, psi	ASTM D-1621	140
Tensile strength, psi	ASTM D-1623	160
K-factor initial, btu in./hr ft²F°	ASTM-C-518	.22
K-factor final, btu in./hr ft²F°	ASTM C-518	.27
Closed Cell Content	ASTM D-1940	>90%
Flame Spread	ASTM E-84	10
Smoke	ASTM E-84	300
Dimensional Stability, 200F°/Ambient RH 28 days	D-2126	0.5%
-20F°/Ambient RH 28 days	D-2126	0%

Processing Characteristics @ 74 ° F

Ratio, By weight A/B		50/50
Cream Time	Sec	45-60
Rise Time	Sec.	200-230
Tack Free Time	Sec	200-230