

test method for measuring moisture vapor emission rate of concrete. ICRI 03732 - Concrete surface preparation.

WOOD

All wood should be clean, dry and free of any knots, splinters, oil, grease or other contaminants. Splintered or rough areas should be sanded. Knots should be repaired using Polycoat Products PC-260 with sand. Upon full cure of the repair agent, prime the entire surface intended for coating.

STEEL (ATMOSPHERIC AND IMMERSION EXPOSURE)

Remove all oil, grease, weld spatters and round off any sharp edges from surface. Minimum surface preparation is Near White Metal Blast Cleaning per SSPC-SP10/NACE 2. Optimum surface profile is 3-4 mils. Prime and shoot Polyeuro® onto any bare metal the same day as it is cleaned to minimize any potential flash rusting.

GALVANIZED SURFACES

Clean and degrease any contaminated surfaces before priming. Do not blast galvanized surfaces with an abrasive grit. An adhesion test is recommended prior to starting the project.

FIBERGLASS REINFORCED PLASTIC

The gel coat should be lightly blasted or sanded with 80 grit sandpaper and cleaned.

PLASTIC FOAMS

Enhanced adhesion is obtained when the foam is mechanically abraded. When coating polystyrene, do not use a solvent-based primer.

TEXTILES, CANVAS, FABRICS

Adhesion to most fabrics, geothermal membranes and textiles does not require a primer.

STAINLESS STEEL

Stainless steel may be grit blasted and degreased before priming. Contact Polycoat Products for recommended primer. Some stainless steel alloys are so inert that it is not possible to achieve a satisfactory bond. An adhesion test is recommended prior to starting the project.

ALUMINUM

Aluminum should be blasted with aluminum oxide or sand, and not with steel or metal grit. Excessive blasting may result in a warped or deformed surface. After blasting, wash aluminum with a commercially available aluminum cleaner. Allow to dry, then prime. Contact Polycoat Products for recommended primer.

NEW AND OLD CAST IRON

Blast with a steel grit and degrease before priming. Old cast iron is difficult to prepare for a satisfactory bond. It can absorb oil and water soluble contaminants that will keep returning to the surface after the coating system has been applied and affect the coating system adhesion. An adhesion test is recommended prior to starting the project.

ALL OTHER SURFACES

An adhesion test is recommended prior to starting the project.

Mixing

Polyeuro® MH752HH may not be diluted under any circumstances. Thoroughly mix Polyeuro® MH752HH Part-B (Resin side) with air driven power equipment until a homogeneous mixture and color is obtained.

Application

Both Part-A and Part-B material should be preconditioned at 80-90°F before application.

Recommended surface temperature must be at least 5°F above the dew point.

Polyeuro® MH752HH should be applied using a plural component, heated, high pressure 1:1 spray mixing equipment like Graco's Reactor, Glass Craft or other equivalent machine may be used.

Both Part-A and Part-B materials should be sprayed at a minimum of 2000 psi and at temperatures above 150°F. Adequate pressure and temperature should be maintained at all times.

Polyeuro® MH752HH should be sprayed in smooth, multi-directional passes to improve uniform thickness and appearance.

Storage

Polyeuro® MH752HH has a shelf life of six (6) months from date of manufacture, in factory-sealed containers.

Part-A and Part-B drums are recommended to be stored above 60°F.

Avoid freezing temperatures.

Store drums on wooden pallets to avoid direct contact with the ground.

If stored for a long period of time, rotate Part-A and Part-B drums regularly.

Limitations

Do not open until ready to use.

Both Part-A and Part-B containers must be fitted with a desiccant device during use.

Warning

This product contains Isocyanates and Curative Material.

Disclaimer: All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the users responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Polycoat Products makes no claim that these tests or any other tests, accurately represent all environments. © 2019 Polycoat Products. All rights reserved. **REV-20190302AA**